

VALOX™ RESIN VIC4311

REGION ASIA

DESCRIPTION

VALOX VIC4311 is a 30% glass filled, impact modified PBT with excellent epoxy adhesion. Automotive underhood applications such as ignition coil housings.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	96	MPa	SABIC - Japan Method
Tensile Strain, break	5 – 5	%	SABIC - Japan Method
Flexural Stress	128	MPa	ASTM D790
Flexural Modulus	6080	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	137	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D648
CTE, -30°C to 30°C	0.00003 – 0.00003	1/°C	TMA
PHYSICAL			
Specific Gravity	1.42	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.07	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
Mold Shrinkage, flow, 6.4 mm	0.6 – 0.8	%	SABIC method
ELECTRICAL			
Surface Resistivity	1.E+16	Ω	ASTM D257
Relative Permittivity, 50/60 Hz	3	-	ASTM D150

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

