



verdant

RRPA610Y

PIR, Reprocessed PA 610, Black

Black, PIR, PA 610

VERDANT RRPA610Y is a post-industrial-recycled, unfilled, polyamide 610 resin in black color intended for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Filler Content	≤ 1.00	%	TGA 2050
Moisture Content	0.01-0.04	%	Loss on Drying
Melting Point	215-224	°C	ASTM D-3418
Tensile Strength	9,200 – 10,200	psi	ASTM D-638

