



verdant

RRPA612Y

PIR, Reprocessed PA 612, Black

Black, PIR, PA 612

VERDANT RRPA612Y is a post-industrial-recycled, unfilled, polyamide 612 resin in black color intended for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Filler Content	0.20-0.80	%	TGA 2050
Moisture Content	0.01-0.04	%	Loss on Drying
Melting Point	215-220	°C	ASTM D-3418
Tensile Strength	9,147 – 10,500	Psi	ASTM D-638

