



verdant

RRPA66 Series

PIR, Reprocessed PA 66, Unfilled

Unfilled, PIR, PA 66

VERDANT RRPA66 Series is a post-industrial-recycled, unfilled, polyamide 66 resin available in mixed color (**VERDANT RRPA66X**), black color (**VERDANT RRPA66Y**), and natural color with lubricant (**VERDANT RRPA66RZ**) intended for compounding applications.

Resin Property	Typical Value	Units	Test Method
Filler Content	0.00-0.80	%	TGA 2050
Moisture Content	0.01-0.10	%	Loss on Drying
Melting Point	250-260	°C	ASTM D-3418
Tensile Strength	10,500 – 12,000	psi	ASTM D-638

