



verdant

RRPA6633GF Series

PIR, Reprocessed PA 66, 33% Glass Filled

Glass filled, PIR, PA 66

VERDANT RRPA6633GF Series is a post-industrial-recycled polyamide 66 resin with 33% glass filler available in mixed color (**VERDANT RRPA6633GFX**) or black color (**VERDANT RRPA6633GFY**) intended for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Filler Content	30-35	%	ASTM D-5630
Moisture Content	0.04-0.10	%	ASTM D-6980
Melting Point	220-225	°C	ASTM D-3418
Tensile Strength	18,000 – 22,000	psi	ASTM D-638
Notched Izod Impact Strength	0.8-1.5	ft-lb/in	ASTM D-256

