



verdant

RRPA6GFX

PIR, Reprocessed PA 6, Glass Filled

Glass filled, PIR, PA 6

VERDANT RRPA6GFX is a post-industrial-recycled polyamide 6 resin with 10-33% glass filler available in mixed color intended for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Filler Content	10-33	%	ASTM D-5630
Melting Point	220-225	°C	ASTM D-3418

