



verdant

RRPC14FX

Regrind Polycarbonate, Unfilled

Melt Flow: 14

VERDANT RRPC14FX is a post-industrial regrind polycarbonate available in mixed color suitable for injection molding.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	14.0	g/10 min	ASTM D-1238
Notched Izod Impact, 23°C (73°F)	>10 (>534)	ft-lb/in (J/m)	ASTM D-256

