



verdant

RRPH0103Z

Recycled Homopolymer Polypropylene

Melt Flow: 1-3

VERDANT RRPH0103Z is a post-industrial, reprocessed, homopolymer polypropylene resin blend in natural color. Typical applications include wood plastic lumber and strapping.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	1.0-3.0	g/10 min	ASTM D-1238
Ash Content, 750 °C	0	%	ASTM D-5630
Tensile Strength	4,300-4,600 (30-32)	psi (MPa)	ASTM D-638

