



verdant

RRPH0710Z

Recycled Homopolymer Polypropylene

Melt Flow: 5-10

VERDANT RRPH0510Z is a post-industrial and post-consumer, reprocessed, homopolymer polypropylene resin blend in natural color.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	7-10	g/10 min	ASTM D-1238
Filler (Ash) Content	0-5	%	Supplier Method (TGA 2050)
Melting Point	315-347 (157-175)	°F (°C)	ASTM D-3418
Polyethylene Content	0-2	%	-

