



verdant

RRPH1015B

Recycled Homopolymer Polypropylene

Melt Flow: 10-15

VERDANT RRPH1015B is a post-industrial, reprocessed, homopolymer polypropylene resin blend available in blue color.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	10-15	g/10 min	ASTM D-1238
Filler Content	0.00-1.00	%	Supplier Method (TGA 2050)
Moisture	0.01-0.10	%	Supplier Method (Loss on Drying)
Tensile Strength	4,400-4,800 (30-33)	psi (MPa)	ASTM D-638

