



verdant

RRPH1126X

Recycled Homopolymer Polypropylene

Melt Flow: 11-26

VERDANT RRP1126X is a post-industrial recycled, reprocessed, homopolymer polypropylene blend in mixed color designed for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	11-26	g/10 min	ASTM D-1238
Ash Content	1.0-3.0	%	ASTM D-5630
Moisture	0.02-0.80	%	Supplier Method (Loss on Drying)
Tensile Strength	4,000-4,700	psi	ASTM D-638
Melting Point	150-170	°C	ASTM D-3418

