



verdant

RRPI0304Y

Recycled Copolymer Polypropylene

Melt Flow: 3-4



VERDANT RRPI0304Y is a post-industrial, reprocessed, copolymer polypropylene resin in black color suitable for injection molding.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	3.0-4.0	g/10 min	ASTM D-1238
Ash Content, 750 °C	0.8-1.5	%	ASTM D-5630
Tensile Strength, 0.02 in/min	3,700-3,900 (26-27)	psi (MPa)	ASTM D-638
Notched Izod Impact, 23°C (73°F), no weights, 1 lb pendulum	12-14 (641-747)	ft-lb/in (J/m)	ASTM D-256

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Data 11/20/2023

