



verdant

RRPI1015Y

Recycled Copolymer Polypropylene

Melt Flow: 10-15

VERDANT RRPI1015Y is a post-industrial, reprocessed, copolymer polypropylene resin suitable for injection molding, available in black color.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	10.0-15.0	g/10 min	ASTM D-1238
Ash Content, 750 °C	2.0-4.0	%	ASTM D-5630
Tensile Strength, 0.02 in/min	3,400-3,800 (23-26)	psi (MPa)	ASTM D-638
Notched Izod Impact, 23°C (73°F)	6.0-8.0 (320-427)	ft-lb/in (J/m)	ASTM D-256

