



VINPOL™ AB0406

Acrylonitrile-Butadiene-Styrene

Melt Flow: 4

Specific Gravity: 1.05

VINPOL AB0406 is a high impact acrylonitrile-butadiene-styrene resin with high gloss and good flow.

Resin Property	Typical Value	Units	Test Method
Melt Flow, 230°C, 3.8 kg	4	g/10 min	ASTM D-1238
Specific gravity	1.05	-	ASTM D-792
Mold Shrinkage, flow, 3.2mm	0.5-0.8	%	Supplier Method
Melt Volume Rate, 220°C/10.0kg	15	cm³/10 min	ISO 1133
Tensile Stress at Yield, Type I, 5mm/min	5,950 (41)	psi (MPa)	ASTM D-638
Tensile Strain at Yield, Type I, 5mm/min	2.1	%	ASTM D-638
Tensile Stress at Break, Type I, 5mm/min	4,500 (31)	psi (MPa)	ASTM D-638
Tensile Strain at Break, Type I, 5mm/min	26	%	ASTM D-638
Flexural Stress at Yield, 1.3mm/min; 50mm span	9,860 (68)	psi (MPa)	ASTM D-790
Flexural Modulus, 1.3mm/min; 50mm span	309,000 (2,130)	psi (MPa)	ASTM D-790
HDT, 0.45 MPa, 3.2mm, unannealed	207 (97)	°F (°C)	ASTM D-648
Vicat Softening Temp., Rate B/50	208 (98)	°F (°C)	ASTM D-1525
CTE, -40°C to 40°C, flow	8.82E-05	1/°C	ASTM E-831
CTE, -40°C to 40°C, xflow	8.64E-05	1/°C	ASTM E-831
Notched Izod Impact Strength, 73° F (23°C)	6.5 (347)	ft-lb/in (J/m)	ASTM D-256
Instrumented Impact Total Energy, 73°F (23°C)	23 (31)	ft-lb (J)	ASTM D-3763
Arc Resistance, Tungsten (PLC)	5	PLC Code	ASTM D-495
Hot Wire Ignition (PLC)	3	PLC Code	UL-746A
High Voltage Arc Track Rate (PLC)	2	PLC Code	UL-746A
High Ampere Arc Ign, surface (PLC)	0	PLC Code	UL-746A
Comparative Tracking Index (UL) (PLC)	0	PLC Code	UL 746A
UL Recognized, 94HB Flame Class Rating	1.52	mm	UL94

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 09/26/2018

