



VinPol™ GP088

Polyethylene Terephthalate

VINPOL GP088 is a PET copolymer with low acetaldehyde generation. It is designed for applications such as 5 gallon blow molded containers.

Resin Property	Typical Value	Units	Test Method
Intrinsic Viscosity	0.880 +/- 0.02	dl/g	Supplier Method
Moisture Content	0.30 max.	wt %	Supplier Method
Ash Content	0.02 max.	wt %	Supplier Method
Acetaldehyde	1.0 max.	ppm	Supplier Method
Color CIE LAB L* b*	91 +/- 2.0 -0.4 +/- 1.0		Supplier Method
Melting Point	245 +/- 3	°C	Supplier Method
Fine Particles	100 max.	ppm	Supplier Method
Bulk Density	0.89 +/- 0.05	g/cm ³	Supplier Method
Size	140 +/- 5.0	pcs/2g	Supplier Method

