



VinPol™ HD00348

High Density Polyethylene

Melt Index: 0.30

Density: 0.948

VINPOL HD00348 is a high performance copolymer designed for non-pressure pipe applications, including conduit, telecommunications and drip irrigation pipe. This grade has good long-term hoop strength performance and outstanding toughness including at low temperatures. It has an excellent balance of stiffness and processability in conduit pipe applications. It meets the requirements of ASTM F2160, UL651A and NEMA TC-7, as well as meeting a minimum ASTM D3350 Cell Classification of 335430A.

Resin Property	Typical Value	Units	Test Method
Melt Index, 2.16 kg at 190°C	0.30	g/10 min	ASTM D-1238
Melt Index, 21.6 kg at 190°C	20	g/10 min	ASTM D-1238
Density	0.948	g/cc	ASTM D-1505
ESCR Condition B (10% Igepal), F10	>96	hrs	ASTM D-1693
ESCR Condition C (100% Igepal), F20	>192	hrs	ASTM D-1693
Tensile Strength at Break, 2 in/min, Type IV bar	3,500 (25)	psi (MPa)	ASTM D-638
Elongation at Break, 2 in/min, Type IV bar	>600	%	ASTM D-638
Flexural Modulus, Tangent, 16:1 span:depth, 0.5 in/min	120,000 (827)	psi (MPa)	ASTM D-790
Brittleness Temperature	-175 (-115)	°F (°C)	ASTM D-746
Hardness	68	Shore D	ASTM D-2240

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 03/24/2020

