



VinPol™ HD09H52

High Density Polyethylene

HLMI: 9

Density: 0.952

VINPOL HD09H52 is a high molecular weight, hexene copolymer HDPE with a bi-modal molecular weight distribution. This resin is suitable for use in high toughness and high stiffness film applications, and also has excellent draw down and bubble stability for producing thin films at high rates. Typical applications include thin films for trash can liners, t-shirt, produce and merchandise bags and roll stock. It is also well positioned in thick films.

Resin Property	Typical Value	Units	Test Method
Melt Index,			
Condition E, 2.16 Kg at 190°C	0.06	g/10 min	ASTM D-1238
Condition F, 21.6 Kg at 190°C (HL)	9.0	g/10 min	ASTM D-1238
Density	0.952	g/cc	ASTM D-4883
Elmendorf Tear Strength, MD/TD	37/83	g	ASTM D-1922
Tensile Strength at Yield, MD/TD	4,500 (31)/3,900 (27)	psi (MPa)	ASTM D-882
Tensile Strength at Break, MD/TD	11,000 (76)/7,000 (48)	psi (MPa)	ASTM D-882
Elongation at Break, MD/TD	>250/>350	%	ASTM D-882
1% Secant Modulus, MD/TD	112,000 (772)/139,000 (958)	psi (MPa)	ASTM D-882
Dart Drop Impact	350	g	ASTM D-1709

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 5/1/2019

