



VinPol™ PR070

Random Copolymer Polypropylene

Melt Flow: 7.0

Density: 0.895

VINPOL PR070 is a low melting, high ethylene random copolymer with improved color, optics, and impact properties. Targeted applications include non-oriented cast film processes for manufacture of packaging films that require improved optical and impact properties, and as a heat seal layer for oriented films. This resin has passed USP Class VI testing, and all ingredients meet the chemical registration requirements of TSCA (U.S.) and DSL (Canada). This resin complies with all applicable FDA regulations for food contact applications.

Resin Property	Typical Value	Units	Test Method
Melt Flow	7.0	g/10 min	ASTM D-1238
Density	0.895	g/cm ³	ASTM D-1505
Ultimate Tensile ¹	3,000 (21)	psi (MPa)	ASTM D-882
Elongation at Break ¹	500	%	ASTM D-882
1% Secant Modulus ¹	70,000 (483)	psi (MPa)	ASTM D-882
MVTR ¹ @ 100°F, 90% RH	0.9	g/100 sq-in/24 hrs/mil	ASTM E-96
Haze ¹	2	%	ASTM D-1003
Gloss, 45° ¹	85	%	ASTM D-2457
Dart Impact (F50) ¹	240	g/mil	ASTM D-1709
Heat Seal Temperature ¹	244 (118)	°F (°C)	SIT ² Supplier Method
Melting Point	275 (135)	°F (°C)	DSC ³ Supplier Method

¹Film properties, Non-Oriented

²Minimum seal strength is 200 g/inch at 15 psi pressure and 1 sec.

³DSC-2 Differential Scanning Calorimeter test procedure available upon request.

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 10/25/2021

