



VINPOL™ PT101

High Melt Strength Co-Polyester

VINPOL PT101 is a co-polyester with high melt strength designed for extrusion blow molding of clear, high-gloss containers capable of being recycled with clear PET. This product is a semi-crystalline PET polymer with high melt strength and slow crystallization allowing for processing on typical extrusion PET blow molding equipment. It has a high melting point with a typical Tg. Containers made from VINPOL PT101 can carry the resin identification code "PETE 1", and can be recycled with the clear PET stream. Containers made from this product are ideal for packaging juice, sports drinks, tea, edible oil, household cleaners, detergents, chemicals and automotive products and can replace containers made from PETG, PVC, PP, PC and HDPE. This product complies with FDA and Cosmetic act for all food packaging applications and certain processing conditions.

Resin Property	Typical Value	Units	Test Method
Intrinsic Viscosity*	1.01 +/- 0.03	dI/g	Supplier Method
Moisture Content (as produced)	0.15 max.	wt %	Karl Fisher Titration
Acetaldehyde	2.0 max.	ppm	Supplier Method
Color L* b*	80.0 min. 1.5 max.		Hunter Colorimeter
Melting Point	240 max.	°C	Supplier method
Fines, through 25 mesh	0.05	%	Supplier Method
Chip Size	2.0 max.	g/100 chips	Supplier Method
Density	1.39 min.	g/cm ³	Supplier Method
**Bulk Density	52 min.	lb/ft ³	Supplier Method

* Determined by conversion of solution viscosity to intrinsic viscosity using an empirical correlation developed by the supplier, equivalent to ASTM D-4603. 1% Solution in Dichloroacetic Acid.

**Not equivalent to bulk density found with fully packed, larger quantities

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 05/10/2022

