

XENOY™ RESIN 1102

REGION AMERICAS

DESCRIPTION

Unreinforced PC/polyester alloy. Excellent low temperature impact/chemical resistance to automotive fluids.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	54	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	150	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1960	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	800	J/m	ASTM D256
Izod Impact, notched, 0°C	690	J/m	ASTM D256
Izod Impact, notched, -30°C	640	J/m	ASTM D256
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	110	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	90	°C	ASTM D648
PHYSICAL			
Specific Gravity	1.19	-	ASTM D792
Specific Volume	0.83	cm³/g	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.8 – 1	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.8 – 1	%	SABIC method
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



petromall.net



info@petromall.ps



+970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840

