

## XENOY™ RESIN 5720

REGION AMERICAS

### DESCRIPTION

UR, PBT+PC alloy. Outstanding low temperature impact /chemical resistance.

### TYPICAL PROPERTY VALUES

Revision 20190702

| PROPERTIES                                   | TYPICAL VALUES                 | UNITS | TEST METHODS |
|----------------------------------------------|--------------------------------|-------|--------------|
| <strong>MECHANICAL</strong>                  |                                |       |              |
| Tensile Stress, yld, Type I, 50 mm/min       | 49                             | MPa   | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min       | 165                            | %     | ASTM D638    |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 68                             | MPa   | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 1720                           | MPa   | ASTM D790    |
| <strong>IMPACT</strong>                      |                                |       |              |
| Izod Impact, unnotched, 23°C                 | 3204                           | J/m   | ASTM D4812   |
| Izod Impact, notched, 23°C                   | 801                            | J/m   | ASTM D256    |
| Izod Impact, notched, -40°C                  | 534                            | J/m   | ASTM D256    |
| Instrumented Dart Impact Energy @ peak, 23°C | 48                             | J     | ASTM D3763   |
| Instrumented Impact Energy @ peak, -40°C     | 55                             | J     | ASTM D3763   |
| <strong>THERMAL</strong>                     |                                |       |              |
| HDT, 0.45 MPa, 6.4 mm, unannealed            | 115                            | °C    | ASTM D648    |
| HDT, 1.82 MPa, 6.4 mm, unannealed            | 96                             | °C    | ASTM D648    |
| Relative Temp Index, Elec                    | 75                             | °C    | UL 746B      |
| Relative Temp Index, Mech w/impact           | 75                             | °C    | UL 746B      |
| Relative Temp Index, Mech w/o impact         | 75                             | °C    | UL 746B      |
| <strong>PHYSICAL</strong>                    |                                |       |              |
| Specific Gravity                             | 1.17                           | -     | ASTM D792    |
| Specific Volume                              | 0.85                           | cm³/g | ASTM D792    |
| Water Absorption, (23°C/24hrs)               | 0.13                           | %     | ASTM D570    |
| Mold Shrinkage, flow, 3.2 mm                 | 1 – 1.2                        | %     | SABIC method |
| <strong>ELECTRICAL</strong>                  |                                |       |              |
| Volume Resistivity                           | 9.5E+16                        | Ω.cm  | ASTM D257    |
| Dielectric Strength, in air, 1.6 mm          | 28.7                           | kV/mm | ASTM D149    |
| Dielectric Strength, in air, 3.2 mm          | 19.8                           | kV/mm | ASTM D149    |
| Relative Permittivity, 100 Hz                | 2.93                           | -     | ASTM D150    |
| Relative Permittivity, 1 MHz                 | 2.95                           | -     | ASTM D150    |
| Dissipation Factor, 100 Hz                   | 0.002                          | -     | ASTM D150    |
| Dissipation Factor, 1 MHz                    | 0.03                           | -     | ASTM D150    |
| <strong>FLAME CHARACTERISTICS</strong>       |                                |       |              |
| UL Yellow Card Link                          | <a href="#">E121562-220839</a> | -     | -            |
| UL Recognized, 94HB Flame Class Rating       | 1.49                           | mm    | UL 94        |
| <strong>INJECTION MOLDING</strong>           |                                |       |              |
| Drying Temperature                           | 110                            | °C    |              |
| Drying Time                                  | 4 – 6                          | Hrs   |              |

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



| PROPERTIES                  | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Drying Time (Cumulative)    | 8              | Hrs   |              |
| Maximum Moisture Content    | 0.02           | %     |              |
| Melt Temperature            | 260 – 275      | °C    |              |
| Nozzle Temperature          | 255 – 270      | °C    |              |
| Front - Zone 3 Temperature  | 255 – 275      | °C    |              |
| Middle - Zone 2 Temperature | 250 – 270      | °C    |              |
| Rear - Zone 1 Temperature   | 245 – 265      | °C    |              |
| Mold Temperature            | 65 – 90        | °C    |              |
| Back Pressure               | 0.3 – 0.7      | MPa   |              |
| Screw Speed                 | 50 – 80        | rpm   |              |
| Shot to Cylinder Size       | 50 – 80        | %     |              |
| Vent Depth                  | 0.013 – 0.02   | mm    |              |

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

