

XENOY™ RESIN 6370

REGION AMERICAS

DESCRIPTION

30% glass-reinforced, impact modified thermoplastic alloy. Improved toughness and ductility.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	97	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	91	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D638
Tensile Modulus, 5 mm/min	9750	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	150	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	138	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5370	MPa	ASTM D790
Hardness, Rockwell R	109	-	ASTM D785
Tensile Stress, yield, 5 mm/min	105	MPa	ISO 527
Tensile Stress, break, 5 mm/min	105	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	8500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	154	MPa	ISO 178
Flexural Modulus, 2 mm/min	7750	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	640	J/m	ASTM D4812
Izod Impact, notched, 23°C	170	J/m	ASTM D256
Izod Impact, notched, -30°C	112	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	5	J	ASTM D3763
Instrumented Dart Impact Total Energy, 23°C	17	J	ASTM D3763
Izod Impact, notched 80°10°4 +23°C	10	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	6	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	9	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	153	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	163	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	204	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	149	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.7E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.1E-04	1/°C	ASTM E831
CTE, 60°C to 138°C, flow	1.98E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	2.7E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.1E-04	1/°C	ISO 11359-2

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	148	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	155	°C	ISO 75/Af
Relative Temp Index, Elec	140	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.44	-	ASTM D792
Specific Volume	0.7	cm³/g	ASTM D792
Water Absorption, (23°C/24hrs)	0.09	%	ASTM D570
Mold Shrinkage, flow, 0.75-2.3 mm	0.3 – 0.4	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	0.4 – 0.5	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	0.4 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	0.7 – 0.9	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	24	g/10 min	ASTM D1238
Density	1.44	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	12	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	19	cm³/10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	4.8E+15	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	20	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	27	kV/mm	ASTM D149
Relative Permittivity, 100 Hz	4	-	ASTM D150
Relative Permittivity, 1 MHz	4	-	ASTM D150
Dissipation Factor, 100 Hz	0.003	-	ASTM D150
Dissipation Factor, 1 MHz	0.02	-	ASTM D150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	3	PLC Code	UL 746A
Comparative Tracking Index {UL} {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-221087	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 280	°C	
Nozzle Temperature	255 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	255 – 275	°C	

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	250 – 270	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 0.6	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

