

XENOY™ RESIN CL101

REGION EUROPE

DESCRIPTION

Xenoy CL101 is an unfilled, impact modified PC/PBT blend with excellent solvent resistance and low-temperature ductility. It has a proven track record in off-line painted exterior automotive applications. ISO1043: PC+PBT-I.

TYPICAL PROPERTY VALUES

Revision 20231003

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	53	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	49	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 50 mm/min	2050	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	75	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2000	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	52	MPa	ISO 527
Tensile Stress, break, 50 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2050	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
Ball Indentation Hardness, H358/30	82	MPa	ISO 2039-1
Hardness, Rockwell L	89	-	ISO 2039-2
IMPACT			
Izod Impact, notched, 23°C	625	J/m	ASTM D256
Izod Impact, notched, 0°C	600	J/m	ASTM D256
Izod Impact, notched, -30°C	450	J/m	ASTM D256
Izod Impact, unnotched 80°10'4 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	50	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	35	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -40°C	25	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	58	kJ/m²	ISO 179/1eA
Charpy Impact, notched, 23°C	30	kJ/m²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80°10'4 sp=62mm	25	kJ/m²	ISO 179/1eA
Charpy Impact, notched, -20°C	25	kJ/m²	ISO 179/2C
Charpy Impact, notched, -30°C	20	kJ/m²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80°10'4 sp=62mm	NB	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10'4 sp=62mm	NB	kJ/m²	ISO 179/1eU
THERMAL			

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	120	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	83	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ASTM E831
Thermal Conductivity	0.18	W/m.°C	ISO 8302
CTE, 23°C to 80°C, flow	9.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	155	°C	ISO 306
Vicat Softening Temp, Rate B/50	120	°C	ISO 306
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	105	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	83	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	83	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.22	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	0.7 – 1.1	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.7 – 1.1	%	SABIC method
Melt Flow Rate, 250°C/5.0 kgf	14	g/10 min	ASTM D1238
Density	1.22	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	13	cm³/10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	>1.E+14	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	18	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.3	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating	1.5	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	255 – 270	°C	
Nozzle Temperature	250 – 265	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	240 – 265	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Hopper Temperature	40 – 60	°C	

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	60 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

PETROMALL

