

XENOY™ RESIN T2RX2500UV

ETP COMPOUND FROM TRUCIRCLE™ PORTFOLIO
REGION AMERICAS

DESCRIPTION

The grade is part of SABIC's TRUCIRCLE™ portfolio and services. XENOY™ T2RX2500UV is a PC/PET blend containing post-consumer recycle. It is a medium viscosity, unfilled, UV stabilized, elastomer modified PC/PET blend with excellent heat and impact performance.

TYPICAL PROPERTY VALUES

Revision 20220314

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	70	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2150	MPa	ISO 178
IMPACT			
Instrumented Dart Impact Total Energy, 23°C	60	J	ASTM D3763
Izod Impact, notched 80°10°4 +23°C	40	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	10	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	50	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10°4 sp=62mm	10	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/120	136	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	108	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80°10°4 sp=64mm	130	°C	ISO 75/Bf
PHYSICAL			
Mold Shrinkage, flow	0.5 – 0.8	%	SABIC method
Mold Shrinkage, xflow	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 265°C/2.16kgf	9	g/10 min	ASTM D1238
Density	1.21	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.7	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 265°C/1.2 kg	4	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 275	°C	
Nozzle Temperature	260 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	250 – 275	°C	

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	240 – 270	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

PETROMALL

