

XENOY™ RESIN T2RX5630Q

ETP COMPOUND FROM TRUCIRCLE™ PORTFOLIO
REGION AMERICAS

DESCRIPTION

The grade is part of SABIC's TRUCIRCLE™ portfolio and services. XENOY™ T2RX5630Q is a 19% mineral filled PC/PET blend containing post-consumer recycle plastics. It has low CTE, high heat, dimensional stability, low shrinkage, especially for painted applications. XENOY™ T2RX5630Q could be positioned for body panels, spoilers, housings, door handles, spring-loaded applications, fuel filler doors, medical device enclosures, EV electric vehicle components.

TYPICAL PROPERTY VALUES

Revision 20220518

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	25	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.3	%	ISO 527
Tensile Strain, break, 5 mm/min	21	%	ISO 527
Tensile Modulus, 1 mm/min	4200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	91	MPa	ISO 178
Flexural Modulus, 2 mm/min	4100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80°10°4 +23°C	120	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10°4 -30°C	80	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	7	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	5	kJ/m²	ISO 180/1A
THERMAL			
CTE, -30°C to 80°C, flow	4.0E-05	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	11.4E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	108	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow	0.5 – 0.7	%	SABIC method
Density	1.35	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.42	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	16	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

