

XENOY™ RESIN X5300WX

REGION ASIA

DESCRIPTION

Unreinforced, opaque PBT+PC alloy. Chemical resistance and good mechanical performance. UV-stabilized. Excellent weatherability.

TYPICAL PROPERTY VALUES

Revision 20180807

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	51	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Tensile Modulus, 50 mm/min	2550	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	96	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2480	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	62	MPa	ISO 527
Tensile Stress, break, 50 mm/min	51	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	110	%	ISO 527
Tensile Modulus, 1 mm/min	2250	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	87	MPa	ISO 178
Flexural Modulus, 2 mm/min	2180	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	747	J/m	ASTM D256
Izod Impact, notched, -30°C	180	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	71	J	ASTM D3763
Izod Impact, notched 80°10°4 +23°C	50	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	15	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	45	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	135	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	101	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	87	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	88	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.02E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.56E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	120	°C	ISO 306
Vicat Softening Temp, Rate B/120	124	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	89	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.23	-	ASTM D792

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 3.2 mm	0.7 – 0.9	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	26	g/10 min	ASTM D1238
Density	1.23	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	25	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

