



TotalEnergies

Refining & Chemicals
Polymers

Polyethylene HDPE XRC20N RT

Technical data sheet
High Density Polyethylene
Produced in Europe

Description

HDPE XRC20N RT is a high performance hexene-based compound primarily intended to protect high-voltage cable.

HDPE XRC20N RT key characteristics are :

- a PE-RT Type II classification (ISO 22391-2)
- a superior resistance to slow crack growth coupled with a MRS of 10 MPa, ensuring safe and durable pipe systems operation (ISO 9080)
- a broad bimodal molecular weight distribution offering outstanding processing properties from small bore pipes to larger diameter pipes extrusion, for both mono- and multilayer applications
- an optimised formulation of additives providing excellent long-term stability in service at elevated temperatures.

Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	kg/m ³	947
Melt Flow Rate (190°C/5 kg)	ISO 1133/T	g/10 min	0.2
Oxidation Induction Time (210 °C)	ISO 11357-6	min	≥ 40
Strain – Hardening test (SHT)	ISO 18488	MPa	≥ 53,0
Cracked Round Bar test (CRB)	ISO 18489	-	≥ 1,5 × 10 ⁶ cycles
Water content (*)	EN 12118	ppm	≤ 300

(*) Measured at the stage of compound manufacturing

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: www.polymers.totalenergies.com.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.

TOTALENERGIES ONE TECH BELGIUM
Zone Industrielle C
B-7181 Feluy
Belgium

Rev : May 24

Page 1 of 1

www.polymers.totalenergies.com

Polyethylene

