

Technical Data Sheet

CAPILENE® CE 71 E

Specialty Polypropylene



Product Description

CAPILENE® CE 71 E is a specialty polypropylene combining typical advantages of polypropylene random and heterophasic copolymers, and is designed for extrusion applications.

Features:	• Excellent impact • Very low stress whitening • Good organoleptic properties • Clarified	• Good transparency • High gloss • Short cycle time
Uses:	• Detergent and cosmetics clear containers • High clarity films	• Corrugated sheets • Profiles
Processing Methods:	• Blow Molding • Sheet extrusion	• Thermoforming

Properties	Method	Typical Value*	Unit
Physical			
Melt Flow Rate	(230°C/2.16 kg) ISO 1133	1.8	g/10 min
Mechanical			
Tensile Stress at Yield	(50 mm/min) ISO 527-2	24	MPa
Tensile Strain at Yield	(50 mm/min) ISO 527-2	21	%
Flexural Modulus	(5 mm/min) ISO 178	850	MPa
Izod Impact Strength, notched	(+23°C) ISO 180	55	kJ/m ²
Izod Impact Strength, notched	(-20°C) ISO 180	4	kJ/m ²
Thermal			
Vicat Softening Temperature	(10 N) ISO 306	135	°C
Heat Deflection Temperature	(0.45 MPa) ISO 75-2	75	°C
Optical			
Haze	(1 mm plaque) ASTM D1003	20	%

*Typical values; not to be construed as specifications.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance and intended for industrial use, to produce plastic articles. Material safety data sheets, international standards certificates and other regulatory documents are available on our website. Carmel Olefins products have not been tested and therefore not validated for use in pharmaceutical/medical applications, and their suitability for these uses cannot be guaranteed. It is the customer's responsibility to test and approve their technical and regulatory suitability in order to satisfy themselves as to the particular purpose and application(s).

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel
Website: <http://www.Carmel-Olefins.co.il>
Email: techserv@caol.co.il

Date: September 2025

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins recommends its customers to review both the manufacturing processes and applications of Carmel Olefins products to ensure, that the products are not used for purposes they are not intended or tested for. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. Data in this document relates only to the specific product and may not be valid for any combination of this product with other materials. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is responsible for its employees' safety and the appropriate, safe and legal use, processing, handling and disposing of our products and packaging. Carmel Olefins shall not be liable for any consequential, incidental or indirect damages resulting from this statement or its use.

