

CYCOLACT™ RESIN FR23

REGION AMERICAS

DESCRIPTION

Flame retardant ABS (non-PBBE additives). Good properties/toughness. Excellent moldability. UL94 V-0 rated.

TYPICAL PROPERTY VALUES

Revision 20190703

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	42	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	35	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.1	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	11	%	ASTM D638
Tensile Modulus, 5 mm/min	2410	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	73	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2720	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	267	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	41	J	ASTM D3763
THERMAL			
Vicat Softening Temp, Rate B/50	90	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	83	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	72	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.92E-05	1/°C	ASTM E831
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.17	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 230°C/3.8 kg	6.8	g/10 min	ASTM D1238
Melt Viscosity, 200°C, 1000 sec-1	3100	Poise	ASTM D3825
Melt Flow Rate, 220°C/5.0 kg	9	g/10 min	ISO 1133
Melt Volume Rate, MVR at 220°C/10.0 kg	37	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220687	-	-
UL Recognized, 94V-0 Flame Class Rating	2.31	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	2.48	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	6	Hrs	
Maximum Moisture Content	0.1	%	

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	200 – 220	°C	
Nozzle Temperature	200 – 220	°C	
Front - Zone 3 Temperature	200 – 215	°C	
Middle - Zone 2 Temperature	195 – 205	°C	
Rear - Zone 1 Temperature	170 – 180	°C	
Mold Temperature	50 – 70	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

