

CYCOLACT™ RESIN GX3800F

REGION ASIA

DESCRIPTION

High impact ABS for sheet extrusion. FDA food contact compliant.

TYPICAL PROPERTY VALUES

Revision 20190703

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	39	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	30	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3.1	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	31.6	%	ASTM D638
Tensile Modulus, 5 mm/min	2080	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	66	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2160	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	432	J/m	ASTM D256
Izod Impact, notched, -30°C	299	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	50	J	ASTM D3763
THERMAL			
Vicat Softening Temp, Rate B/50	106	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	93	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.01E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.04E-04	1/°C	ASTM E831
PHYSICAL			
Specific Gravity	1.03	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Melt Viscosity, 240°C, 100 sec-1	14000	Poise	ASTM D3825
Melt Volume Rate, MVR at 220°C/ 10.0 kg	4	cm³/ 10 min	ISO 1133
EXTRUSION BLOW MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	4 – 5	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature (Parison)	215 – 230	°C	
Barrel - Zone 1 Temperature	205 – 225	°C	
Barrel - Zone 2 Temperature	205 – 225	°C	
Barrel - Zone 3 Temperature	205 – 225	°C	
Barrel - Zone 4 Temperature	205 – 225	°C	
Adapter - Zone 5 Temperature	210 – 230	°C	
Head - Zone 6 - Top Temperature	215 – 230	°C	
Head - Zone 7 - Bottom Temperature	215 – 230	°C	

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	20 – 60	rpm	
Extruder Feed Zone Temperature	60 – 75	°C	
Mold Temperature	40 – 80	°C	
Die Temperature	215 – 235	°C	
SHEET EXTRUSION			
Drying Temperature	80 – 95	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	215 – 260	°C	
Barrel - Zone 1 Temperature	170 – 200	°C	
Barrel - Zone 2 Temperature	180 – 220	°C	
Barrel - Zone 3 Temperature	190 – 225	°C	
Barrel - Zone 4 Temperature	200 – 240	°C	
Adapter Temperature	205 – 250	°C	
Die Temperature	205 – 250	°C	
Roll Stack Temp - Top	90 – 95	°C	
Roll Stack Temp - Middle	95 – 105	°C	
Roll Stack Temp - Bottom	100 – 105	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

