

CYCOLACT™ RESIN INP562

REGION AMERICAS

DESCRIPTION

Low flow powder SAN for color concentrates and alloys. FDA compliant (part use must be at room temperature or below).

TYPICAL PROPERTY VALUES

Revision 20210607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	74	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	74	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.9	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.9	%	ASTM D638
Tensile Modulus, 5 mm/min	3830	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	103	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3780	MPa	ASTM D790
Hardness, Rockwell R	121	-	ASTM D785
Tensile Stress, yield, 50 mm/min	78	MPa	ISO 527
Tensile Stress, break, 50 mm/min	78	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.2	%	ISO 527
Tensile Strain, break, 50 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	3950	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	74	MPa	ISO 178
Flexural Modulus, 2 mm/min	3460	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	22	J/m	ASTM D256
Izod Impact, notched, -30°C	23	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	2	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	2	kJ/m²	ISO 180/1A
Charpy Impact, notched, 23°C	1	kJ/m²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm	97	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	84	°C	ASTM D648
Vicat Softening Temp, Rate B/50	104	°C	ISO 306
Vicat Softening Temp, Rate B/120	106	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	86	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D792
Melt Flow Rate, 230°C/3.8 kg	6.4	g/10 min	ASTM D1238
Density	1.08	g/cm³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	16	g/10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	90	%	ASTM D1003
Haze, 2.54 mm	1.8	%	ASTM D1003

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

