

CYCOLACT™ RESIN INP572

REGION MEA

DESCRIPTION

Low flow SAN pellets, FDA compliant (part use must be at room temperature or below).

TYPICAL PROPERTY VALUES

Revision 20220619

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Flexural Stress, yld, 1.3 mm/min, 50 mm span	134	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3900	MPa	ASTM D790
Flexural Stress, yield, 2 mm/min	92	MPa	ISO 178
Flexural Modulus, 2 mm/min	3460	MPa	ISO 178
IMPACT			
Charpy Impact, unnotched, 23°C	1	kJ/m ²	ISO 179/2C
Izod Impact, notched, 23°C	46	J/m	ASTM D256
Izod Impact, notched 80°10°4 +23°C	3	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	2	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	95	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	85	°C	ASTM D648
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	105	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	87	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D792
Melt Flow Rate, 230°C/3.8 kg	5.8	g/10 min	ASTM D1238
Density	1.08	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	16	g/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	75 – 85	°C	
Drying Time (Cumulative)	2 – 4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	190 – 220	°C	
Nozzle Temperature	190 – 220	°C	
Front - Zone 3 Temperature	190 – 210	°C	
Middle - Zone 2 Temperature	180 – 200	°C	
Rear - Zone 1 Temperature	170 – 190	°C	
Mold Temperature	50 – 70	°C	
Screw Speed	40 – 70	rpm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



petromall.net



info@petromall.ps



+970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840

