

CYCOLACT™ RESIN MG29

REGION ASIA

DESCRIPTION

Super high impact ABS. Good low temperature toughness.

TYPICAL PROPERTY VALUES

Revision 20190924

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	39	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	31	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.4	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	26	%	ASTM D638
Tensile Modulus, 5 mm/min	2000	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	65	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2070	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	42	MPa	ISO 527
Tensile Stress, break, 50 mm/min	32	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.8	%	ISO 527
Tensile Strain, break, 50 mm/min	20	%	ISO 527
Tensile Modulus, 1 mm/min	2050	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	61	MPa	ISO 178
Flexural Modulus, 2 mm/min	1990	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	455	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	29	J	ASTM D3763
Izod Impact, notched 80°10'4 +23°C	37	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	12	kJ/m²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	99	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	79	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.54E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.36E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/50	98	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10'4 sp=64mm	79	°C	ISO 75/Af
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.04	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 230°C/3.8 kg	1.2	g/10 min	ASTM D1238
Melt Viscosity, 240°C, 1000 sec-1	2800	Poise	ASTM D3825

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 220°C/10.0 kg	8	g/10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 95	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	230 – 275	°C	
Nozzle Temperature	230 – 275	°C	
Front - Zone 3 Temperature	225 – 240	°C	
Middle - Zone 2 Temperature	210 – 220	°C	
Rear - Zone 1 Temperature	190 – 200	°C	
Mold Temperature	50 – 65	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

