

CYCOLACT™ RESIN MG37EPX

REGION AMERICAS

DESCRIPTION

ABS plating grade optimized for a broad processing window for both painted and plated applications, NSF standard 61 compliant (80 sq in/L)

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	44	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	54	%	ASTM D638
Tensile Modulus, 5 mm/min	2470	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2810	MPa	ASTM D790
Hardness, Rockwell R	106	-	ASTM D785
Tensile Stress, yield, 5 mm/min	48	MPa	ISO 527
Tensile Stress, break, 5 mm/min	39	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	18.3	%	ISO 527
Tensile Modulus, 1 mm/min	2760	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	73	MPa	ISO 178
Flexural Modulus, 2 mm/min	2470	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	250	J/m	ASTM D256
Izod Impact, notched, -40°C	88	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	35	J	ASTM D3763
Izod Impact, notched 80°10'4 +23°C	23	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	8	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -40°C	6	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	88	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	76	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	98	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10'4 sp=64mm	82	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.05	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 230°C/3.8 kg	6.6	g/10 min	ASTM D1238
Melt Viscosity, 240°C, 1000 sec-1	2170	Poise	ASTM D3825
Density	1.05	g/cm³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	22	g/10 min	ISO 1133
FLAME CHARACTERISTICS			

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Yellow Card Link	E121562-100896040	-	-
UL Recognized, 94HB Flame Class Rating	1.52	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80 – 95	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	255 – 280	°C	
Nozzle Temperature	255 – 280	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	215 – 230	°C	
Mold Temperature	40 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	
Shot to Cylinder Size	50 – 70	%	
Vent Depth	0.038 – 0.051	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

