

## CYCOLACT™ RESIN MG38

REGION ASIA

### DESCRIPTION

Very high impact ABS. Toughness/rigidity. Good fatigue resistance.

### TYPICAL PROPERTY VALUES

Revision 20190924

| PROPERTIES                                   | TYPICAL VALUES | UNITS    | TEST METHODS |
|----------------------------------------------|----------------|----------|--------------|
| <strong>MECHANICAL</strong>                  |                |          |              |
| Tensile Stress, yld, Type I, 5 mm/min        | 44             | MPa      | ASTM D638    |
| Tensile Stress, brk, Type I, 5 mm/min        | 33             | MPa      | ASTM D638    |
| Tensile Strain, yld, Type I, 5 mm/min        | 2.1            | %        | ASTM D638    |
| Tensile Strain, brk, Type I, 5 mm/min        | 26             | %        | ASTM D638    |
| Tensile Modulus, 5 mm/min                    | 2270           | MPa      | ASTM D638    |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 72             | MPa      | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 2340           | MPa      | ASTM D790    |
| <strong>IMPACT</strong>                      |                |          |              |
| Izod Impact, notched, 23°C                   | 373            | J/m      | ASTM D256    |
| Instrumented Dart Impact Total Energy, 23°C  | 31             | J        | ASTM D3763   |
| <strong>THERMAL</strong>                     |                |          |              |
| Vicat Softening Temp, Rate B/50              | 98             | °C       | ASTM D1525   |
| HDT, 0.45 MPa, 3.2 mm, unannealed            | 97             | °C       | ASTM D648    |
| HDT, 1.82 MPa, 3.2mm, unannealed             | 82             | °C       | ASTM D648    |
| CTE, -40°C to 40°C, flow                     | 8.82E-05       | 1/°C     | ASTM E831    |
| CTE, -40°C to 40°C, xflow                    | 8.64E-05       | 1/°C     | ASTM E831    |
| Relative Temp Index, Elec                    | 60             | °C       | UL 746B      |
| Relative Temp Index, Mech w/impact           | 60             | °C       | UL 746B      |
| Relative Temp Index, Mech w/o impact         | 60             | °C       | UL 746B      |
| <strong>PHYSICAL</strong>                    |                |          |              |
| Specific Gravity                             | 1.05           | -        | ASTM D792    |
| Mold Shrinkage, flow, 3.2 mm                 | 0.5 – 0.8      | %        | SABIC method |
| Melt Flow Rate, 230°C/3.8 kg                 | 3.7            | g/10 min | ASTM D1238   |
| Melt Viscosity, 240°C, 1000 sec-1            | 2450           | Poise    | ASTM D3825   |
| Melt Flow Rate, 220°C/10.0 kg                | 15             | g/10 min | ISO 1133     |
| <strong>ELECTRICAL</strong>                  |                |          |              |
| Arc Resistance, Tungsten {PLC}               | 5              | PLC Code | ASTM D495    |
| Hot Wire Ignition {PLC}                      | 3              | PLC Code | UL 746A      |
| High Voltage Arc Track Rate {PLC}            | 2              | PLC Code | UL 746A      |
| High Ampere Arc Ign, surface {PLC}           | 0              | PLC Code | UL 746A      |
| Comparative Tracking Index (UL) {PLC}        | 0              | PLC Code | UL 746A      |
| <strong>FLAME CHARACTERISTICS</strong>       |                |          |              |
| UL Recognized, 94HB Flame Class Rating       | 1.52           | mm       | UL 94        |
| <strong>INJECTION MOLDING</strong>           |                |          |              |
| Drying Temperature                           | 80 – 95        | °C       |              |

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



| PROPERTIES                  | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Drying Time                 | 2 – 4          | Hrs   |              |
| Drying Time (Cumulative)    | 8              | Hrs   |              |
| Maximum Moisture Content    | 0.1            | %     |              |
| Melt Temperature            | 220 – 260      | °C    |              |
| Nozzle Temperature          | 220 – 260      | °C    |              |
| Front - Zone 3 Temperature  | 215 – 240      | °C    |              |
| Middle - Zone 2 Temperature | 205 – 225      | °C    |              |
| Rear - Zone 1 Temperature   | 190 – 210      | °C    |              |
| Mold Temperature            | 50 – 70        | °C    |              |
| Back Pressure               | 0.3 – 0.7      | MPa   |              |
| Screw Speed                 | 30 – 60        | rpm   |              |
| Shot to Cylinder Size       | 50 – 70        | %     |              |
| Vent Depth                  | 0.038 – 0.051  | mm    |              |

#### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

