



Formosa Plastics®

Formolene® PP

Formolene® 6300C

Impact Copolymer for Pipe Extrusion Applications

Formolene® 6300C is a fractional melt flow high impact copolymer designed for non-pressure pipe but can also be used for high melt strength extrusion applications requiring an excellent balance of toughness and stiffness. It is designed to be suitable for corrugated pipe application and meets ASTM F2881 and AASHTO M330 requirements.

This material is free of animal-derived content.

Typical Properties of this Commercial Grade

Property	Test Method	Typical Values	
		English	SI
Melt Flow Rate, I ₂ @ 230°C	ASTM D1238	0.3 g/10 min	0.3 g/10 min
Density	ASTM D1505	0.9 g/cm ³	0.9 g/cm ³
Tensile Strength at Yield (50 mm/min)	ASTM D638	4,800 psi	33 MPa
Elongation at Yield (50 mm/min)	ASTM D638	8 %	8 %
Flexural Modulus (1.3 mm/min), 1% Sec.	ASTM D790	230 kpsi	1590 MPa
Notched Izod Impact Strength @ 73° F	ASTM D256A	No break	No break
Notched Izod Impact Strength @ -4° F	ASTM D256A	1 ft-lb/in	55 J/m
Heat Deflection Temperature @ 66 psi	ASTM D648	240 °F	115 °C
Heat Deflection Temperature @ 264 psi	ASTM D648	136 °F	58 °C
Tensile Creep Modulus	ASTM D6992	>40 kpsi	>275 MPa

Specimens were injection molded according to the conditions specified in ASTM D4101. Data for representative purposes only; n ot to be construed as product specification. Published 05/23. Updated 07/25

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® is a registered trademark of FPC USA

10/15

