



Formosa Plastics®

Formolene® LDPE

Formolene® FC3403C

Clarity LDPE Resin with no Slip or Antiblock

Formolene® FC3403C is a low density polyethylene offering good balance of optical properties and high stiffness.

Formolene® FC3403C is formulated without slip and antiblock for use in applications offering excellent extrusion processing and good balance of film stiffness and optical properties.

Suggested Applications:

Cast Film	Hygiene Packaging	Paper Overwrap
Co-Extrusion Films	Label Film	
Embossed Films	Overwrap Film	

Nominal Physical Properties:

PROPERTY	TEST METHOD	UNIT	VALUE
Density	D792	g/cc	0.934
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min	3.0
Dart Impact	D1709	g	60
Elmendorf Tear Strength	D1922	g	100/170*
Tensile Strength at Yield	D882	psi	2200/2200*
Tensile Strength at Break	D882	psi	3200/2600*
Elongation at Break	D882	%	430/560*
Secant Modulus @ 1%	D882	psi	54000/54000*
Gloss (45°)	D2457		73
Haze	D1003	%	6.0

* MD / TD

Note: Film properties based on 1.18 mil (30 micron) thick film using a 7.9 in (200 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 284 - 338°F (140 - 170°C), a 39.4 mil (1.0 mm) die gap. Actual film properties may vary based on extrusion equipment, operating conditions and additive package. Film properties are not intended to be used as specifications.

Published 07/15/19

