



Formosa Plastics®

Formolene® LLDPE

Formolene FORMAX® L91904B

High Strength Linear Low Density Polyethylene for Sheet Extrusion Applications

Formolene FORMAX® L91904B is a linear low density, high molecular weight hexene copolymer resin that is tailored specifically for geomembrane applications. The resin provides outstanding ESCR properties, broad fusion range, excellent melt strength and good processability.

Suggested Applications:

Landfill Covers
Coextrusion

Flat and round-die products

Nominal Physical Properties:

PROPERTY	TEST METHOD	UNIT	VALUE
Density	D1505	g/cc	0.918
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min	0.5
Tensile Yield Strength			
2 in. per min., Type IV bar	D638	psi	1600
Elongation at Break			
2 in. per min., Type IV bar	D638	%	700
Flexural Modulus, Tangent –			
16:1 span:depth, 0.5 in./min.	D790	psi	65,000
Durometer Hardness,			
Type D (Shore D)	D2240	Shore D	55
Vicat Softening Temperature			
Loading 1, Rate A	D1525	°C	100
Heat Deflection Temperature,			
66 psi., Method A	D648	°C	49
ESCR			
Condition B (10% Igepal), F ₅₀	D1693	h	>3,000
Condition C (100% Igepal), F ₅₀	D1693	h	>3,000

The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purpose.

Published 06/01/2020

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® & Formolon® are registered trademarks of FPC USA

02/20

