

GELOY™ RESIN CR7520

REGION ASIA

DESCRIPTION

ASA. Profile and Sheet. Excellent weatherability, good flow/aesthetics and high impact.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	41	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	34	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	40	%	ASTM D638
Tensile Modulus, 50 mm/min	1790	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	58	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1790	MPa	ASTM D790
Hardness, Rockwell R	86	-	ASTM D785
IMPACT			
Izod Impact, notched, 23°C	320	J/m	ASTM D256
Izod Impact, notched, -30°C	58	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	25	J	ASTM D3763
THERMAL			
Vicat Softening Temp, Rate B/50	99	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	87	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	76	°C	ASTM D648
HDT, 1.82 MPa, annealed	95	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	90	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	79	°C	ASTM D648
CTE			
-40°C to 40°C, flow	8.64E-05	1/°C	ASTM E831
-40°C to 40°C, xflow	9.18E-05	1/°C	ASTM E831
-30°C to 0°C, flow	8.46E-05	1/°C	ASTM E831
0°C to 100°C, flow	9.E-05	1/°C	ASTM E831
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.06	-	ASTM D792
Water Absorption, (23°C/Saturated)	0.55	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate			
220°C/10.0 kgf	7	g/10 min	ASTM D1238
260°C/5.0 kgf	13	g/10 min	ASTM D1238
OPTICAL			
Gloss, untextured, 60 degrees	95	-	ASTM D523

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
ELECTRICAL			
Surface Resistivity	>1.E+15	Ω	ASTM D257
Dielectric Strength, in oil, 3.2 mm	15.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	5.2	-	ASTM D150
Relative Permittivity, 1 MHz	3.21	-	ASTM D150
Dissipation Factor			
50/60 Hz	0.15	-	ASTM D150
1 MHz	0.026	-	ASTM D150
Hot Wire Ignition (PLC)	3	PLC Code	UL 746A
High Ampere Arc Ign, surface (PLC)	0	PLC Code	UL 746A
Comparative Tracking Index (UL) (PLC)	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-100072245	-	-
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
UV-light, water exposure/immersion	F2	-	UL 746C
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 6	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	240 – 270	°C	
Nozzle Temperature	240 – 270	°C	
Front - Zone 3 Temperature	240 – 270	°C	
Middle - Zone 2 Temperature	225 – 260	°C	
Rear - Zone 1 Temperature	220 – 250	°C	
Mold Temperature	55 – 75	°C	
Back Pressure	0.7 – 1.4	MPa	
Screw Speed	30 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

