

GELOY™ RESIN XP4034

REGION EUROPE

DESCRIPTION

PC/ASA. Excellent weatherability.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	120	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	35	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
Ball Indentation Hardness, H358/30	98	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched 80°10°4 +23°C	33	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	8	kJ/m²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	107	°C	ISO 306
Vicat Softening Temp, Rate B/120	109	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120°10°4 sp=100mm	112	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120°10°4 sp=100mm	100	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.4 – 0.6	%	SABIC method
Density	1.15	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.7	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.25	%	ISO 62
Melt Volume Rate			
260°C/5.0 kg	15	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Yellow Card Link	F45329-100370046	-	-
INJECTION MOLDING			
Drying Temperature	90 – 105	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	260 – 275	°C	
Mold Temperature	50 – 70	°C	

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



petromall.net



info@petromall.ps



+970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840

