

## التصنيع TASNEE

### TASNEE HD B1258

### POLYETHYLENE

#### DESCRIPTION

**TASNEE HD B1258** is a High Density Polyethylene with an excellent combination of stiffness and environmental stress crack resistance (ESCR). It is delivered in pellet form.

#### TYPICAL APPLICATION

Designed for small blow molding containers up to 5 liters for food and consumer applications.

| TYPICAL PROPERTIES                               | METHOD        | UNIT              | VALUE |
|--------------------------------------------------|---------------|-------------------|-------|
| <b>Physical</b>                                  |               |                   |       |
| Density                                          | ISO 1183-1    | g/cm <sup>3</sup> | 0.958 |
| Melt Flow Rate (190°C/2.16 kg)                   | ISO 1133-1    | g/10 min          | 0.30  |
| Melt Flow Rate (190°C/5.0 kg)                    | ISO 1133-1    | g/10 min          | 1.2   |
| Melt Flow Rate (190°C/21.6 kg)                   | ISO 1133-1    | g/10 min          | 22    |
| <b>Mechanical</b>                                |               |                   |       |
| Tensile Modulus                                  | ISO 527-1, -2 | MPa               | 1320  |
| Tensile Stress @ Yield                           | ISO 527-1, -2 | MPa               | 28    |
| Tensile Strain @ Yield                           | ISO 527-1, -2 | %                 | 10    |
| FNCT (3.5 MPa, 2% Arkopal N 100, 80°C)           | ISO 16770     | hr                | 8     |
| <b>Impact</b>                                    |               |                   |       |
| Charpy Impact Strength-Notched @ -30°C           | ISO 179/1eA   | kJ/m <sup>2</sup> | 6.5   |
| Tensile Impact Strength-Notched @ -30°C          | ISO 8256      | kJ/m <sup>2</sup> | 75    |
| <b>Hardness</b>                                  |               |                   |       |
| Shore Hardness (Shore D)                         | ISO 868       |                   | 63    |
| Ball Indentation Hardness (H 132/30)             | ISO 2039-1    | MPa               | 53    |
| <b>Thermal</b>                                   |               |                   |       |
| Vicat Softening Temperature (B50 (50°C/hr, 50N)) | ISO 306       | °C                | 79    |

**Recommended Temperatures:**  
Melt temperature: 180°C - 220°C

**Note:** The above properties values are not to be construed as specifications.



## التصنيع TASNEE

### Food Contact

The material is manufactured to the highest standards but, special requirements apply to certain applications, such as food contact end-use. For specific information on regulatory compliance, please contact TASNEE below or our local representative in your area.

### Safety

Workers should be protected from the possibility of skin or eye contact with molten polymer. As minimum precaution, safety glasses and heat resistance gloves are suggested to prevent mechanical or thermal injury to eyes and hands. Molten polymer exceeding processing condition requirements may degrade and release, fumes, vapors and unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes and vapors. Legislation on the control of emissions and pollution prevention must be observed. If the principles of sound manufacturing practice are adhered to and the place of work is well ventilated, no health hazards are involved in processing the material.

The material may burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. In burning the material generates considerable heat and may release a dense black smoke. Fires should be extinguished by heavy foams or dry powder. For further information about safety in handling and processing please refer to the Safety Data Sheet (SDS).

### Storage

The material is packed in 25 kg bags or in bulk containers protecting it from contamination. Storage time of material longer than 6 months may have a negative influence on the quality of the final product. It is generally recommended to convert all materials latest within 6 months from delivery date. The material is subjected to degradation by ultra-violet radiation or by high storage temperatures. Therefore, the material must be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Further unfavorable storage conditions are large fluctuations in ambient temperature and high atmospheric humidity. TASNEE will not give any warranty to unfavorable storage conditions which may lead to quality deterioration such as color change, bad smell and inferior product performance.

### Disclaimer

"The information and data contained in this document is submitted without prejudice, and is based on our current knowledge, experience and on a limited number of tests". "In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties nor of suitability for a specific purpose of the products made with or on the basis of the information in this document".

