

TECHNICAL DATA SHEET

TRICOLENE LDF06919B

Low Density Polyethylene

777 Post Oak Blvd, Suite 550,
Houston TX, USA - 77056
+1-713-963-0066
www.triconenergy.com



ADDING A WORLD OF VALUE

PRODUCT DESCRIPTION

This type of Medium-Heavy Duty LDPE is a high molecular weight homopolymer of ethylene produced in a polymerization process using a tubular reactor. This reference has an antiblock additive.

PROCESSING METHODS

Blown Film Extrusion

CHARACTERISTICS

Good Mechanical Properties
Excellent Bubble Stability

APPLICATIONS

Industrial Shrink Film
Heavy Duty Bags

RESIN PROPERTIES	TEST METHOD	VALUES, English Units	VALUES, International Units
Melt Flow Rate 2.16 kgf/190 °C MFR ₂	ASTM D1238	0.60 g/10 min	0.60 g/10 min
Density 23 °C	ASTM D1505	0.919 g/cm ³	0.919 g/cm ³
Antiblock	---	4,000 ppm	4,000 ppm
Antioxidant Package	---	Yes	Yes

RESIN PROPERTIES	TEST METHOD	VALUES, English Units	VALUES, International Units
Evaluated Film Thickness	---	2.0 mils	50.8 µm
Dart Impact Strength	ASTM D1709A	130 g/mil F50	130 g/25.4 µm F50
23 °C, 1.5 in (38.0 mm), 26.0 in (0.66 m), F50			
Tensile Strength at Break	ASTM D882	MD 3,700 psi	25.5 MPa
20.0 in/min (508 mm/min)		TD 2,900 psi	20.0 MPa
Tensile Elongation at Break	ASTM D882	MD 280 %	280 %
20.0 in/min (508 mm/min)		TD 740 %	740 %
Tensile Secant Modulus of Elasticity	ASTM D882	MD 29,000 psi	200.0 MPa
1 % Elongation, 0.051 in/min (1.3 mm/min)		TD 34,500 psi	237.9 MPa
Haze	ASTM D1003	7.5 %	7.5 %
Specular Gloss 45 °	ASTM D2457	62.0	62.0

PROCESSING CONDITIONS OF EVALUATED FILM	VALUES, English Units	VALUES, International Units
Die Gap	35 mils	0.9 mm
Blow-up Ratio, BUR	2.5 ---	2.5 ---

The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications. No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

REGULATORY COMPLIANCE

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used in such applications.

