

TECHNICAL DATA SHEET

TRICOLENE LDF2923B

Low Density Polyethylene

777 Post Oak Blvd, Suite 550,
Houston TX, USA - 77056
+1-713-963-0066
www.triconenergy.com



ADDING A WORLD OF VALUE

PRODUCT DESCRIPTION

This type of LDPE is a homopolymer of ethylene. This reference has an antiblock additive.

PROCESSING METHODS

Blown Film Extrusion
Cast Film Extrusion

CHARACTERISTICS

High Optical Properties
Good Processability
Stiffness

APPLICATIONS

High Clarity Packaging
Lamination Films

RESIN PROPERTIES

Melt Flow Rate 2.16 kg/190 °C MFR₂
Density 23 °C
Antiblock
Antioxidant Package

TEST METHOD

ASTM D1238
ASTM D1505

VALUES, ENGLISH UNITS

2.0 g/10 min
0.923 g/cm³
1,000 ppm
Yes

VALUES, INTERNATIONAL UNITS

2.0 g/10 min
0.923 g/cm³
1,000 ppm
Yes

BLOWN FILM PROPERTIES

Evaluated Film Thickness
Dart Impact Strenght
38.0 mm (1.5 in), 0.66 m (26.0 in), F50

TEST METHOD

ASTM D1709A

VALUES, ENGLISH UNITS

1.5 mils
90 g

VALUES, INTERNATIONAL UNITS

38.1 µm
90 g

Elmendorf Tear Strenght

ASTM D1922

MD 290 g
TD 190 g

290 g
190 g

Tensile Strenght at Yield
20.0 in/min (508 mm/min)

ASTM D882

MD 1,500 psi
TD 1,600 psi

10 MPa
11 MPa

Tensile Strenght at Break
20.0 in/min (508 mm/min)

ASTM D882

MD 3,400 psi
TD 2,800 psi

23 MPa
19 MPa

Tensile Elongation at Break
20.0 in/min (508 mm/min)

ASTM D882

MD 180 %
TD 510 %

180 %
510 %

Haze

ASTM D1003

5.1 %

5.1 %

Specular Gloss 45 °

ASTM D2457

78.0

78.0

PROCESSING CONDITIONS OF EVALUATED FILM

Die Diameter
Die Gap
Melt Temperature
Blow-up Ratio, BUR
Specific Output

VALUES, ENGLISH UNITS

2.5 in
30 mils
350 °F
2.5 ---
8.00 Lb/h/in

VALUES, INTERNATIONAL UNITS

64 mm
0.8 mm
177 °C
2.5 ---
1.43 kg/h/cm

The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications. No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

REGULATORY COMPLIANCE

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used in such applications.

Revision 1: 2020-11-04

FLEXIBLE

