

TECHNICAL DATA SHEET

TRICOLENE LLB2918SB

Linear Low Density Polyethylene

777 Post Oak Blvd, Suite 550,
Houston TX, USA - 77056
+1-713-963-0066
www.triconenergy.com



ADDING A WORLD OF VALUE

PRODUCT DESCRIPTION

This type of LLDPE is a copolymer of ethylene and 1-butene produced with Ziegler-Natta catalysts in a gas phase polymerization process.

PROCESSING METHODS

Blown Film (Co)Extrusion
Cast Film (Co)Extrusion

CHARACTERISTICS

Toughness and Strength
Sealing Properties

APPLICATIONS

Cast Stretch Film
Packaging Blown Films

RESIN PROPERTIES

Melt Flow Rate 2.16 kg/190 °C

MFR₂

TEST METHOD

ASTM D1238

VALUES, ENGLISH UNITS

2.0 g/10 min

VALUES, INTERNATIONAL UNITS

2.0 g/10 min

Density 23 °C

ASTM D1505

0.918 g/cm³

0.918 g/cm³

Slip

1,500 ppm

1,500 ppm

Antiblock

6,300 ppm

6,300 ppm

Antioxidant Package

Yes

Yes

FILM PROPERTIES *

TEST METHOD

VALUES, ENGLISH UNITS

VALUES, INTERNATIONAL UNITS

Evaluated Film Thickness

1.0 mils

25.4 µm

Dart Impact Strenght

ASTM D1709A

100 g

100 g

38.0 mm (1.5 in), 0.66 m (26.0 in), F50

Elmendorf Tear Strenght

ASTM D1922

MD

110 g

110 g

TD

330 g

330 g

Tensile Strenght at Yield

ASTM D882

MD

1,500 psi

10 MPa

TD

1,500 psi

10 MPa

Tensile Strenght at Break

ASTM D882

MD

4,600 psi

32 MPa

TD

3,600 psi

25 MPa

Tensile Elongation at Break

ASTM D882

MD

660 %

660 %

TD

700 %

700 %

Tensil Secant Modulus of Elasticity

ASTM D882

MD

24,700 psi

170 MPa

TD

27,600 psi

190 MPa

1 % Elongation, 0.051 in/min (1.3 mm/min)

Haze

ASTM D1003

14.0 %

14.0 %

Specular Gloss 45 °

ASTM D2457

43.0

43.0

PROCESSING CONDITIONS OF THE EVALUATED FILM

TEST METHOD

VALUES, ENGLISH UNITS

VALUES, INTERNATIONAL UNITS

Die Diameter

4.0 in

102 mm

Die Gap

100 mils

2.5 mm

Blow-up Ratio, BUR

2.5 ---

2.5 ---

* The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications.

No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

REGULATORY COMPLIANCE

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used in such applications.

