

TECHNICAL DATA SHEET

TRICOLENE mLLH35918

Linear Low Density Polyethylene
Metallocene

777 Post Oak Blvd, Suite 550,
Houston TX, USA - 77056
+1-713-963-0066
www.triconenergy.com



ADDING A WORLD OF VALUE

PRODUCT DESCRIPTION

This type of mLLDPE is a copolymer of ethylene and 1-hexene produced with Metallocene catalysts in a gas phase polymerization process.

PROCESSING METHODS

Cast Film Extrusion

CHARACTERISTICS

High Puncture Resistance
High Stretchability
High Unitization Holding Force

APPLICATIONS

Cast Stretch Films
Lamination Films
Cast Hygiene Films

RESIN PROPERTIES

Melt Flow Rate 2.16 kg/190 °C MFR₂
Density 23 °C
Antioxidant Package

ASTM D1238

ASTM D1505

VALUES, ENGLISH UNITS

3.3 g/10 min

0.918 g/cm³

Yes

VALUES, INTERNATIONAL UNITS

3.3 g/10 min

0.918 g/cm³

Yes

CAST FILM PROPERTIES

Evaluated Film Thickness

Dart Impact Strenght

38.0 mm (1.5 in), 0.66 m (26.0 in), F50

ASTM D1709A

1.0 mils
150 g

25.4 µm
150 g

Elmendorf Tear Strenght

ASTM D1922

MD 197 g
TD 517 g

197 g
517 g

Tensile Strenght at Yield

20.0 in/min (508 mm/min)

ASTM D882

MD 1,242 psi
TD 1,138 psi

8.6 MPa
7.8 MPa

Tensile Strenght at Break

20.0 in/min (508 mm/min)

ASTM D882

MD 10,657 psi
TD 7,155 psi

73.5 MPa
49.3 MPa

Tensile Elongation at Break

20.0 in/min (508 mm/min)

ASTM D882

MD 550 %
TD 720 %

550 %
720 %

Haze

ASTM D1003

2.4 %

2.4 %

PROCESSING CONDITIONS OF EVALUATED FILM

Melt Temperature

VALUES, ENGLISH UNITS

455 ° F

VALUES, INTERNATIONAL UNITS

235 ° C

The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications. No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

REGULATORY COMPLIANCE

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used in such applications.

Revision 3: 2021-12-09

FLEXIBLE

