

VALOX™ FR RESINS 364

REGION ASIA

DESCRIPTION

VALOX 364 is an unreinforced, impact modified flame retardant Polybutylene Terephthalate/Polycarbonate (PBT/PC) injection moldable flame grade. It has excellent chemical resistance and a UL94V0@1.47mm and 5VA@3.0mm flame rating. This is a good candidate for outdoor applications in telecommunications enclosures.

TYPICAL PROPERTY VALUES

Revision 20190628

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	46	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	36	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	50	%	ASTM D638
Tensile Modulus, 5 mm/min	1960	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	66	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1800	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	46	MPa	ISO 527
Tensile Stress, break, 50 mm/min	36	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	36	%	ISO 527
Tensile Modulus, 1 mm/min	1950	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	69	MPa	ISO 178
Flexural Modulus, 2 mm/min	1830	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	747	J/m	ASTM D256
Izod Impact, notched, -20°C	694	J/m	ASTM D256
Izod Impact, notched, -40°C	427	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	45	J	ASTM D3763
Instrumented Impact Total Energy, -20°C	44	J	ASTM D3763
Instrumented Impact Total Energy, -40°C	47	J	ASTM D3763
Izod Impact, notched 80°10'4 +23°C	51	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	17	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	51	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	115	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	103	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	68	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	9.8E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	9.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	119	°C	ISO 306
Vicat Softening Temp, Rate B/120	122	°C	ISO 306

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	74	°C	ISO 75/Af
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.3	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.8 – 1	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.8 – 1	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	19	g/10 min	ASTM D1238
Density	1.31	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.09	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
Melt Volume Rate, MVR at 265°C/5.0 kg	17	cm³/10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E207780-548318	-	-
UL Recognized, 94V-0 Flame Class Rating	1.47	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	2.99	mm	UL 94
Oxygen Index (LOI)	28	%	ASTM D2863
UV-light, water exposure/immersion	F2	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 265	°C	
Nozzle Temperature	245 – 260	°C	
Front - Zone 3 Temperature	250 – 265	°C	
Middle - Zone 2 Temperature	245 – 260	°C	
Rear - Zone 1 Temperature	240 – 255	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



petromall.net



info@petromall.ps



+970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840

