

VALOX™ FR RESINS DR48

REGION EUROPE

DESCRIPTION

VALOX DR48 is a 17% glass filled, flame retardant Polybutyleneterephthalate (PBT) injection moldable grade with excellent chemical resistance. It has a UL94V0@0.90mm and 5VA@3.0mm flame rating. This is a good candidate for a variety of applications in the electrical industry including connectors, bobbins, and switches.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	93	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	93	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Tensile Modulus, 5 mm/min	7100	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	140	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	140	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5200	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	16	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	104	MPa	ISO 527
Tensile Stress, break, 5 mm/min	104	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	7000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	155	MPa	ISO 178
Flexural Stress, break, 2 mm/min	155	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3	%	ISO 178
Flexural Modulus, 2 mm/min	6100	MPa	ISO 178
Ball Indentation Hardness, H358/30	218	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	24	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	24	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	500	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	275	J/m	ASTM D4812
Izod Impact, notched, 23°C	49	J/m	ASTM D256
Izod Impact, notched, 0°C	45	J/m	ASTM D256
Izod Impact, notched, -30°C	45	J/m	ASTM D256
Izod Impact, unnotched 80°10°4 +23°C	20	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10°4 -30°C	20	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 0°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	5	kJ/m ²	ISO 179/1eA

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy Impact, notched, 23°C	5	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -30°C	5	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	25	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	20	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	218	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	199	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	190	°C	ASTM D648
Thermal Conductivity	0.19	W/m·°C	ISO 8302
CTE, -40°C to 40°C, flow	2.83E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.95E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	3.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.57E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.49E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	218	°C	ISO 306
Vicat Softening Temp, Rate B/50	198	°C	ISO 306
Vicat Softening Temp, Rate B/120	199	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	215	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	185	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	180	°C	ISO 75/Af
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.53	-	ASTM D792
Filler Content	17	%	ASTM D229
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.8	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.6 – 0.9	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	90	g/10 min	ASTM D1238
Density	1.51	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.17	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	14	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	40	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	70	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	105	Pa·s	ISO 11443
ELECTRICAL			
Volume Resistivity	1.0E+15	Ω.cm	ASTM D257
Dielectric Strength, in oil, 0.8 mm	29	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	ASTM D149

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	ASTM D149
Relative Permittivity, 1 MHz	3.4	-	ASTM D150
Dissipation Factor, 1 MHz	0.016	-	ASTM D150
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Volume Resistivity	1.0E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.0E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	19	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 0.8 mm	29	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.1	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.012	-	IEC 60250
Comparative Tracking Index	175	V	IEC 60112
Comparative Tracking Index, M	150	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.2	-	IEC 60250
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-103127446	-	-
UL Yellow Card Link 2	E45329-236616	-	-
UL Recognized, 94V-0 Flame Class Rating	0.9	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	3.0	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	31	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

