

VALOX™ FR RESINS V6750

REGION EUROPE

DESCRIPTION

VALOX™ V6750 resin is a 25% glass fiber reinforced, non-Chlorinated/non-Brominated/non-Antimony (Sb₂O₃) flame-retardant Polybutylene Terephthalate (PBT) injection molding grade. It is compliant with UL94 V0 @ 0.75mm and CTI 425V (IEC) / PLC1 (ASTM). This resin is based on No Intentionally Added PFAS (referred as NIA PFAS). Good candidate for various Electrical & Electronic (E&E) and E-Mobility Automotive applications, like (High Voltage) connectors, busbars, switches and electrical housings.

TYPICAL PROPERTY VALUES

Revision 20251126

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	115	MPa	ISO 527
Tensile Stress, break, 5 mm/min	115	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.4	%	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	9800	MPa	ISO 527
Flexural Stress	180	MPa	ISO 178
Flexural Stress, yield, 2 mm/min	180	MPa	ISO 178
Flexural Stress, break, 2 mm/min	180	MPa	ISO 178
Flexural Modulus, 2 mm/min	9250	MPa	ISO 178
Tensile Stress, yld, Type I, 5 mm/min	115	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.5	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D638
Tensile Modulus, 5 mm/min	9800	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	9800	MPa	ASTM D790
IMPACT			
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	42	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	50	kJ/m ²	ISO 179/1eU
Izod Impact, notched, 23°C	70	J/m	ASTM D256
Izod Impact, unnotched, 23°C	670	J/m	ASTM D4812
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/120	210	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Af
HDT, 1.82 MPa, 3.2mm, unannealed	210	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
CTE, 23°C to 150°C, flow	2.40E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.42E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
CTE, 23°C to 150°C, flow	2.40E-05	1/°C	ASTM E831
CTE, 23°C to 150°C, xflow	1.42E-04	1/°C	ASTM E831

© 2025 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Density	1.52	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
Water Absorption, (23°C/saturated)	0.06	%	ISO 62-1
Melt Volume Rate, MVR at 250°C/5.0 kg	21	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	38	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	142	Pa-s	ISO 11443
Mold Shrinkage on Tensile Bar, flow	0.1 – 0.5	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 1.0	%	SABIC method
Specific Gravity	1.52	-	ASTM D792
Filler Content	25	%	ASTM D229
Melt Flow Rate, 250°C/5.0 kgf	36	g/10 min	ASTM D1238
ELECTRICAL			
Comparative Tracking Index	425	V	IEC 60112
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-104704473	-	-
UL Recognized, 94V-0 Flame Class Rating	0.75	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	2	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	0.75	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 0.75 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	750	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	240 – 265	°C	
Nozzle Temperature	235 – 260	°C	
Front - Zone 3 Temperature	240 – 265	°C	
Middle - Zone 2 Temperature	235 – 260	°C	
Rear - Zone 1 Temperature	230 – 255	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



petromall.net



info@petromall.ps



+970 599 2020 64



Hebron - Palestine

فلسطين - الخليل

+972 2 2233840

