

VALOX™ RESIN 310

REGION AMERICAS

DESCRIPTION

Unreinforced, general purpose. Typical viscosity 5000-7000.

TYPICAL PROPERTY VALUES

Revision 20190628

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	51	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	300	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	82	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D790
Hardness, Rockwell R	117	-	ASTM D785
IMPACT			
Izod Impact, unnotched, 23°C	1602	J/m	ASTM D4812
Izod Impact, notched, 23°C	53	J/m	ASTM D256
Gardner, 23°C	40	J	ASTM D3029
Modified Gardner, 23°C	40	J	ASTM D3029
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	154	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	54	°C	ASTM D648
CTE, -40°C to 40°C, flow	8.1E-05	1/°C	ASTM E831
CTE, 60°C to 138°C, flow	1.39E-04	1/°C	ASTM E831
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.31	-	ASTM D792
Specific Volume	0.76	cm³/g	ASTM D792
Water Absorption, (23°C/24hrs)	0.08	%	ASTM D570
Mold Shrinkage, flow, 0.75-2.3 mm	0.9 – 1.6	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	1.5 – 2.3	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	1 – 1.7	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	1.6 – 2.4	%	SABIC method
Melt Viscosity	600	Pa-s	SABIC method
ELECTRICAL			
Volume Resistivity	>4.E+16	Ω.cm	ASTM D257
Dielectric Strength, in air, 1.6 mm	23.2	kV/mm	ASTM D149
Dielectric Strength, in air, 3.2 mm	15.7	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	23.2	kV/mm	ASTM D149
Dielectric Strength, in oil, 3.2 mm	15.7	kV/mm	ASTM D149

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Permittivity, 100 Hz	3.3	-	ASTM D150
Relative Permittivity, 1 MHz	3.1	-	ASTM D150
Dissipation Factor, 100 Hz	0.002	-	ASTM D150
Dissipation Factor, 1 MHz	0.02	-	ASTM D150
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220783	-	-
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	240 – 255	°C	
Front - Zone 3 Temperature	245 – 260	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.013 – 0.025	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

