

VALOX™ RESIN 325

REGION EUROPE

DESCRIPTION

General purpose, unreinforced, improved processing. Applications like sprinklers and nozzles, pumps, door handle, tank covers, pens, pencils etc.

TYPICAL PROPERTY VALUES

Revision 20240702

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	51	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	35	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	250	%	ASTM D638
Tensile Modulus, 50 mm/min	2400	MPa	ASTM D638
Taber Abrasion, CS-17, 1 kg	9	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2100	MPa	ISO 178
Ball Indentation Hardness, H358/30	135	MPa	ISO 2039-1
Hardness, Rockwell R	118	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	NB	kJ/m²	ISO 179/2C
Charpy Impact, unnotched, -30°C	NB	kJ/m²	ISO 179/2C
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	1240	J/m	ASTM D4812
Izod Impact, notched, 23°C	53	J/m	ASTM D256
Izod Impact, notched, 0°C	50	J/m	ASTM D256
Izod Impact, notched, -30°C	50	J/m	ASTM D256
Izod Impact, unnotched 80°10'4 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	6	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 0°C	6	kJ/m²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	6	kJ/m²	ISO 180/1A
Charpy Impact, notched, 23°C	6	kJ/m²	ISO 179/2C
Charpy Impact, notched, -30°C	5	kJ/m²	ISO 179/2C
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	175	°C	ASTM D1525
Thermal Conductivity	0.16	W/m·°C	ISO 8302
CTE, 23°C to 80°C, flow	1.3E-04	1/°C	ISO 11359-2

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 80°C, xflow	1.3E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	175	°C	ISO 306
Vicat Softening Temp, Rate B/120	175	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	115	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	50	°C	ISO 75/Af
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
PHYSICAL			
Specific Gravity	1.31	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow	1.1 – 2	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.9 – 1.8	%	SABIC method
Melt Flow Rate, 265°C/5.0 kgf	50	g/10 min	ASTM D1238
Melt Flow Rate, 266°C/5.0 kgf	50	g/10 min	ASTM D1238
Density	1.31	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.34	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	14	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	30	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	48	cm³/10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	215	Pas	ISO 11443
ELECTRICAL			
Volume Resistivity	>1.E+15	Ω.cm	ASTM D257
Dielectric Strength, in oil, 0.8 mm	31	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	ASTM D149
Dielectric Strength, in oil, 3.2 mm	15.7	kV/mm	ASTM D149
Relative Permittivity, 1 MHz	3.1	-	ASTM D150
Dissipation Factor, 1 MHz	0.02	-	ASTM D150
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, shorttime, 1.0mm	16	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 0.8 mm	31	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.1	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0003	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Comparative Tracking Index, M	350	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.9	-	IEC 60250
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45329-236588	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94HB Flame Class Rating 2nd value	3	mm	UL 94
Glow Wire Flammability Index 750°C, passes at	3.2	mm	IEC 60695-2-12
Glow Wire Flammability Index 850°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	21	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

